

MATERIAL & FINISH CODE

TURBO CODE	MILITARY CODE	MATERIAL	PLATING	PROCESS	ROHS COMPLIANT
A	A	ALUMINIUM	ANODIZING BLACK	AMS-A-8625 Type II Class 2, 336 Hour Salt Spray, Non-Conductive -65 to +175°C	YES
AH	-	ALUMINIUM	ANODIZE - HARDCOAT BLACK	AMS-A-8625 Type III, Class 2, .001 thick, 336 Hour Salt Spray, Non-Conductive -65 to +200°C	YES
N	N	ALUMINIUM	ELECTROLESS NICKEL	AMS-C-26074 Class 4 Grade B; ASTM-B-733, SC 2, Type IV, 48 Hour Salt Spray, Conductive -65 to +200°C	YES
W	W	ALUMINIUM	CADMIUM - OLIVE DRAB	SAE-AMS-QQ-P-416 Type II Class 2 over electroless nickel 500 Hour Salt Spray, Conductive -65 to +175°C	NO
WS	W	ALUMINIUM	CADMIUM - OLIVE DRAB	SAE-AMS-QQ-P-416 Type II Class 2 over electroless nickel 1000 Hour Salt Spray, Conductive -65 to +175°C"	NO
Z	Z	ALUMINIUM	ZINC NICKEL - BLACK	ASTM B841 Grade 5 over electroless nickel 1000 Hour Salt Spray, Conductive -65 to +175°C	NO
VB	-	ALUMINIUM	ZINC COBALT - BLACK	ASTM B 840 Grade 6 Type D over electroless nickel 350 Hour Salt Spray, Conductive -65 to +175°C	YES
VO	-	ALUMINIUM	ZINC COBALT - OLIVE DRAB	ASTM B 840 Grade 6 Type D over electroless nickel, 350 Hour Salt Spray, Conductive -65 to +175°C	YES
NU	-	MARINE BRONZE	UNPLATED	1000 Hour Salt Spray, Conductive -65 to +200°C	YES
NS	-	MARINE BRONZE	SHOT BLASTED	1000 Hour Salt Spray, Conductive -65 to +200°C	YES
S	S	STAINLESS STEEL	PASSIVATION	SAE-AMS-SAE-AMS-QQ-P-35 Type VI 1000 Hour Salt Spray, Conductive -65 to +200°C	YES
BC	B	STAINLESS STEEL	CADMIUM BLACK	SAE-AMS-QQ-P-416 Type II Class 3 1000 Hour Salt Spray, Conductive -65 to +175°C	NO

List doesn't exhaust. More finishes can be provided as per demand. Please notify your requirement on sales@turboindia.co.in, our sales team will get back to you on your queries.